CAT. A

1044/15, 1039/15, 1039/930, 1040/24, 1033/929

| CARATTERISTICHE GENERALI · *GENERAL CHARACTERISTICS* | VALORI · *VALUES* | | | | UNITÀ · *UNITS* | NORMATIVE · *STANDARDS* |
|---|---|---|---|---|---|---|
| Altezze · *Width* | 152 | | | | cm | |
| Peso · *Weight* | 270 (± 5%) | | | | gr/m$^2$ | |
| Composition · *Composition* | 100% Fibra Acrilica outdoor tinta in massa<br>100% solution-dyed acrylic | | | | | |
| Carico alla rottura · *Breaking load* | Ordito · *Warp* | 1.900 | Trama · *Weft* | 800 | N | UNI EN ISO 13934 – 1 |
| Allungamento · *Elongation* | Ordito · *Warp* | 28,0 | Trama · *Weft* | 23,0 | % | |
| Impermeabilità · *Permeability* | ISO 5 (100) | | | | | UNI EN 24920 |
| Usura Martindale · *Abrasion ( Martindale)* | Valore medio *Average value* 17.000 | | | | N° cicli · N° cycles | UNI EN ISO 12947 – 2 |
| Tenuta alla cucitura · *Sewing (resistance)* | Ordito · *Warp* | 180 N<br>4 | Trama · *Weft* | 180 N<br>3 | mm | UNI EN ISO 13936-2 |
| Pilling al martindale | Valore medio 4 a 2.000 cicli *Average value 4 at 2.000 cycles* | | | | | UNI EN ISO 12945 - 2 |
| Solidità dei colori alle intemperie artificiali prova con lampada ad arco allo xeno<br>*Colour fastness to artificial weathering Xenon are fading lamp test* | grado 7/8 – 8 scala dei blu<br>grado 4/5 dopo 1000 ore di esposizione scala dei grigi<br>*7/8 – 8 degree blue scale*<br>*degree 4/5 after 1000 hour of exposure on the grey scale* | | | | | EN ISO 105 – B04 |
| Finissaggio · *Finishing* | Idrorepellente con trattamento PFAS free<br>*Water-repellent with PFAS freefinishing* NON PFAS | | | | | |
| ISTRUZIONI DI LAVAGGIO · *CARE* | | | | | | |
| Istruzioni per la pulizia<br>*Cleaning instructions* | Non strizzare o torcere, non stirare a vapore. E' sempre consigliabile agire rapidamente sulle macchie per evitare un lungo contatto che consentirebbe alle sostanze di penetrare nel tessuto, rendendo così più difficile la pulizia. Può essere lavato a secco o in lavatrice a 30° con un detersivo delicato, una centrifugazione a bassa velocità e fatto successivamente asciugare all'aria. Non usare l'asciugatrice. Se necessario, stirare ad una temperatura massima di 110°<br>Qualora sul tessuto fossero presenti macchie a base grassa (olio, maionese ecc..) è necessario intervenire tempestivamente: per la rimozione della singola macchia, dopo aver tamponato ed eliminato la sostanza grassa, si può utilizzare un prodotto a base solvente seguendo le indicazioni del produttore (trielina commerciale o schiuma a base solvente). Il tessuto è lavabile a secco. Se sul tessuto si depositano sostanze come resine di alberi o simili (dove può crescere la muffa), è consigliabile trattare il tessuto strofinando delicatamente l'area interessata con una soluzione di candeggina (ipoclorito di sodio) – non candeggina delicata – diluendo 1 parte di candeggina in 4 parti di acqua. Dopo questo trattamento è sempre necessario risciacquare accuratamente il tessuto e lasciarlo asciugare all'ombra per evitare ingiallimenti.<br>*Do not twist or wring, do not steam iron. It is always advisable to take action soon on stains to avoid long contact that would allow the substance to penetrate into the fibres, so making it more difficult to spot-clean. Fabrics can be dry-cleaned or washed in a washing machine with a gentle 30°C cycle, with soft detergent, low speed spin dry, then air dry. Do not use a tumble dryer. If required, dry-iron with a maximum temperature of 110°C*<br>*If grease-based stains (oil, mayonnaise, etc.) are present on Tempotest Home® fabric, they must be promptly cleaned: for the removal of a single stain, after blotting and removing the greasy substance, a solvent-based product can be used according to the manufacturer's instructions (commercial trichloroethylene or solvent-based foam). Fabric is dry-cleanable. If substances like tree resin or similar (where mould can grow) are deposited on the fabric, it is advisable to treat fabric by gently rubbing the affected area with a solution of bleach containing sodium hypochlorite – not gentle bleach - diluted 1 part bleach to 4 parts water.*<br>*After this treatment, it is always necessary to rinse the fabric thoroughly and then let it dry in the shade to avoid any yellowing effect.* | | | | | |

CERTIFICAZIONI *CERTIFICATIONS:*

OEKO TEX® STANDARD 100 971521.0 CENTROCOT www.oeko-tex.com

Idrorepellente
*Water-repellent*