CAT. B
TLDI

CARATTERISTICHE GENERALI · *GENERAL CHARACTERISTICS*	VALORI · *VALUES*	UNITÀ · *UNITS*	NORMATIVE *STANDARDS*
Composition · *Composition*	37% CO - 55% VI - 8% LI		
Peso · *Weight*	950	gr/ml	
	679 +/-5%	gr/sqm	
Ripetizione ordito · *Repeat warp*	13	cm	
Ripetizione trama · *Repeat weft*	4	cm	
Altezze · *Width*	140 +/-3%	cm	
RESISTENZA DEL TESSUTO · *FABRIC RESISTANCE*			
Abrasione martindale · martindale abrasion	27.000 +/- 10%	*giri/ cycles*	UNI EN ISO 12947-2:2000
Pilling	4 (change at 5000 turns)		UNI EN ISO 12945-2:2002
Solidità al lavaggio a secco · Dry clean fastness	4-5		UNI EN ISO D01:1995
Solidità allo sfregamento a secco · Rub fastness dry	4-5		UNI EN ISO 105-X12:1995
Solidità allo sfregamento a umido · Rub fastness wet	2-3		UNI EN ISO 105-X12:1995
Solidità alla luce colori chiari · Light fastness light colour	4-5		UNI EN ISO 105-B02
Solidità alla luce colori medio-scuri · Light fastness medium-dark colour	5		UNI EN ISO 105-B02
REAZIONE AL FUOCO / FIRE BEHAVIOR			
BS 5852-1 (1979) MATCH			
*CAL TB 117:2013 FAIL**			
NOTE · *NOTES*			
*CAL TB 117:2013 fail: SECTION 2. BARRIER MATERIALS TEST Upholstery cover fabrics that fail the cover fabric test described in Section 1 can be used in upholstered furniture if a barrier (interliner) material that passes this test method is used. When a barrier is required- the barrier material must cover all sides and top of the seating cushion(s). Exceptions: Non-reversible and non-detachable seating cushions do not require the use of the barrier material on the underside of the seating cushion.			
ISTRUZIONI DI LAVAGGIO · *CARE*			