CAT. B
TLLI

CARATTERISTICHE GENERALI · *GENERAL CHARACTERISTICS*	VALORI · *VALUES*	UNITÀ · *UNITS*	NORMATIVE *STANDARDS*
Composition · *Composition*	68% VI - 29% CO - 3% LI		
Peso · *Weight*	1.000	gr/ml	
	714	gr/sqm	
Altezze · *Width*	140 +/- 10%	cm	
RESISTENZA DEL TESSUTO · *FABRIC RESISTANCE*			
Abrasione martindale · martindale abrasion	27.000 +/- 10%	*giri/ cycles*	UNI EN ISO 12947-2:2000
Pilling	3-4 (change at 5000 turns)		UNI EN ISO 12945-2:2002
Solidità al lavaggio a secco · Dry clean fastness	4-5		UNI EN ISO D01:1995
Solidità allo sfregamento a secco · Rub fastness dry	4-5		UNI EN ISO 105-X12:1995
Solidità allo sfregamento a umido · Rub fastness wet	2-3		UNI EN ISO 105-X12:1995
Solidità alla luce colori chiari · Light fastness light colour	4-5		UNI EN ISO 105-B02
Solidità alla luce colori medio-scuri · Light fastness medium-dark colour	5		UNI EN ISO 105-B02
REAZIONE AL FUOCO / FIRE BEHAVIOR			
*BS 5852-1 (1979) MATCH***			
*CAL TB 117:2013 FAIL**			
NOTE · *NOTES*			
*CAL TB 117:2013 fail: SECTION 2. BARRIER MATERIALS TEST Upholstery cover fabrics that fail the cover fabric test described in Section 1 can be used in upholstered furniture if a barrier (interliner) material that passes this test method is used. When a barrier is required- the barrier material must cover all sides and top of the seating cushion(s). Exceptions: Non-reversible and non-detachable seating cushions do not require the use of the barrier material on the underside of the seating cushion. **BS5852-1 (1979) MATCH: Cover fabric containing at least 75% by weight of cotton- flax- viscose- modal- silk or wool- used separately or together and not coated with polyurethane or a polyurethane preparation. Cover fabric shall be used with a fire resistant interliner meeting the requirements of schedule 3 of Statutory Instrument. In this situation- the conformity of match test according to Part I of schelule 5 of statutory instument is not necessary.			
ISTRUZIONI DI LAVAGGIO · *CARE*			